

## Technical Data Sheet



# CLEARCOAT SPRAY 1C

## VARNISH

- 1 component acrylic varnish in spraycan
- For treating varnished surfaces with the purpose of adjusting the gloss or protecting metallic colors.
- Available in matt 30%, semi-gloss 70% and high-gloss 85%

### TECHNICAL PROPERTIES

- Dust dry in 5 minutes, manageable in 30 minutes and completely dry after 2 hours.
- Direct adhesion on the Duthoo 1C lacquers after 30 minutes and before 3 hours, and on powdercoatings after pretreatment with the Duthoo Etching Promotor.
- Yield: 0,7-1 m<sup>2</sup> per spraycan for a dry layer thickness of 25/30μ.
- Good resistance to UV, does not turn yellow.
- Good flexibility.
- Scratch resistant.
- Sustainable resistance to household maintenance products at normal use.
- Professional use.

### USE

- The surfaces must be free of any impurities.
- Pretreatment of the hardened, painted surface with Duthoo Etching Promoter OR paint the 1C metallic after at least 30 min of drying and before 3 hours of drying.
- Shake spraycan well before use (2 to 3 minutes). Spray at a distance of 20-25 cm.
- Apply in several thin wet coats until the desired thickness is reached.
- The spraycan contains 2 nozzles: 1 flat jet and 1 round jet.
- Avoid use at temperature below 15 ° c and in extreme heat or humidity.
- To promote the retention time of your spraycan, hold your spraycan upside down and spray until no more paint comes out. Store upside down.

### PACKAGING

400 ML SPRAYCAN